


# Trident Marine

## Specifications



<b>ORIGIN</b>	Malaysia
<b>SPECIES</b>	Kedondong (Canatium)
<b>CORE</b>	Mersawa / Medang / Kelat
<b>FACE/BACK</b>	Kedondong (Canatium)
<b>GRADE</b>	B/BB
<b>FINISH</b>	Raw
<b>SIZE</b>	48" x 96"
<b>VENEER CUT</b>	Rotary Cut, WPF
<b>VENEER THICKNESS</b>	0.8mm
<b>SURFACE SANDING</b>	150-240 grit finish
<b>GLUE TYPE</b>	WBP EPA Certified
<b>MOISTURE CONTENT</b>	10%-14%
<b>APPLICATIONS</b>	Boats, ships, docks, baths, kitchens, decks, patios, porches



THICKNESS	# OF PLYS	THICKNESS VARIATION	SHEETS PER CRATE
12mm	7	11.5mm-12.3mm	78
18mm	9	17.5mm-18.3mm	52



TRIDENT MARINE FOLLOWS ALL GUIDELINES PER STANDARD GRADING BS 1088.

Based on availability, USply reserves the right to substitute product that may vary in species, core, country of origin, and/or other specifications.

# Trident Marine

## Standard Grading BS 1088



NATURAL DEFECTS		
NUMBER	CATEGORY OF DEFECT	BB
1	Burls	Permitted
2	Pin Knots	Permitted
3	Live Knots	Permitted, 5 per m2 from face. Max dia. 25mm and not clustered
4	Knot Holes	Permitted, max dia. 9mm, cumulative diameter <40 m2 and puttied
5	Color Variation	Permitted, not many
6	Stain/Mineral Streaks	Permitted, not many
7	Dry Pitch and Back Pocket	Permitted, Light 1 per m2, max width 4mm and max length 100mm
8	Wormholes, Pinholes, Worm Tracks	Permitted, small, no color change and not long, puttied
9	Vine Marks	Permitted, not many, lightly sanded and smooth
10	Joints	Permitted, max 3 joints, open width max 3mm and max length 10% of panels length and puttied
11	Splits-Open	Permitted
12	Splits - Fried or Puttied	Permitted, max 2 per panel on panel end, max width 5mm max length 12.5% of panel length
13	Fill or Fatty Smears	Permitted, slight and smooth sanded
14	Rough Cut	Permitted, slight
15	Shims	Permitted, max 5mm, length 300mm, tight and color match
16	Knife Marks	Permitted, width 0.8mm and slight
17	Tape/Glue Residue	Permitted, slight and smooth sanded
18	Sanding	Permitted, slight
19	Chicken Tracks	Permitted

Based on availability, USply reserves the right to substitute product that may vary in species, core, country of origin, and/or other specifications.